

Material Characteristics



Commercial Name: Prima Porphyry Violet Mix
Stone Type: Mixed / Porphyry
Place of Origin: Trentino / Italy



Characteristics	Value	Test standard
Flexural Strength (MPa) LEV	21.00	BS EN 12372:2006
Slip Resistance	Unpolished: 61	BS EN 14231:2003
Water Absorption (%)	0.70	BS EN 13755:2008
Wide Wheel Abrasion (mm)	14	BS EN 14157:2004
PPV (Before/After Polishing)	73/53 (Natural Cleft)	BS EN 7932:2003



Ethical Trading Initiative
Respect for workers worldwide



Federation
stone
Great Britain

Hardscape North (Registered office) Eagley House, Deakins Business Park, Egerton, Bolton, Lancashire, BL7 9RP
Hardscape Midlands - Sales - 1st & 2nd Floor, Guild House, Packwood Court, Guild Street, Stratford Upon Avon, CV37 6RP
Hardscape Midlands - Production - Unit 25, Long Marston Industrial Estate, Long Marston, Stratford Upon Avon, CV37 8QR
Hardscape South - 59 Warwick Way, Pimlico, London, SW1V 1QR
Hardscape Scotland - 44 Charlotte Square, Edinburgh, EH2 4HQ
Hardscape Ireland - Building C The Studios, 89 Holywood Road, Belfast, BT4 3BD
Telephone 01204 565 500 **Email** enq@hardscape.co.uk

www.hardscape.co.uk