

Material Characteristics



Commercial Name: Tower Blue
 Stone Type: Grey / Sandstone
 Place of Origin: Shandong / China



Characteristics	Value	Test standard
Flexural Strength (MPa) LEV	16.70	BS EN 12372:2006
Flexural Strength freeze / thaw resistance before and after (MPa) MEAN	20.4 / 20.2	BS EN 12371:2010
Compressive Strength (MPa) LEV	119.00	BS EN 1926:2006
Compressive Strength freeze / thaw resistance before and after (MPa) MEAN	148 / 129	BS EN 12371:2010
Slip Resistance	Flamed: 81 (Wet) BH: 86 (wet)	BS EN 14231:2003
Water Absorption (%)	2.60	BS EN 13755:2008
Wide Wheel Abrasion (mm)	24.8	BS EN 14157:2004
Open Porosity (%)	5.6	BS EN 1936:2006



Hardscape North (Registered office) Eagley House, Deakins Business Park, Egerton, Bolton, Lancashire, BL7 9RP
Hardscape Midlands - Sales - 1st & 2nd Floor, Guild House, Packwood Court, Guild Street, Stratford Upon Avon, CV37 6RP
Hardscape Midlands - Production - Unit 25, Long Marston Industrial Estate, Long Marston, Stratford Upon Avon, CV37 8QR
Hardscape South - 59 Warwick Way, Pimlico, London, SW1V 1QR
Hardscape Scotland - 44 Charlotte Square, Edinburgh, EH2 4HQ
Hardscape Ireland - Building C The Studios, 89 Holywood Road, Belfast, BT4 3BD
Telephone 01204 565 500 **Email** enq@hardscape.co.uk

www.hardscape.co.uk