

Material Characteristics



Commercial Name: Classic
 Stone Type: Mid Grey / Granite
 Place of Origin: Fujian / China
 Density (Kg/m3): 2760



Characteristics	Value	Test standard
Flexural Strength (MPa) LEV	17.30	BS EN 12372:2006
Flexural Strength freeze / thaw resistance before and after (MPa) MEAN	19.6 / 18.1	BS EN 12371:2010
Compressive Strength (MPa) LEV	155.00	BS EN 1926:2006
Compressive Strength freeze / thaw resistance before and after (MPa) MEAN	172 / 162	BS EN 12371:2010
Slip Resistance	Flamed: 70 (wet), 80 (dry) Bush-Hammered: 78 (wet), 90 (dry)	BS EN 14231:2003
Water Absorption (g/m2/s2)	0.18	BS EN 13755:2008
Wide Wheel Abrasion (mm)	19.2	BS EN 14157:2004
Open Porosity (%)	0.6	BS EN 1936:2006
PPV (Before/After Polishing)	x	BS EN 7932:2003
Light Reflectance Value (LRV) %	37.3 (Flamed), 21.5 (Honed), 44.0 (Bush-Hammered)	BS EN 84369:2008



Hardscape Products Ltd., Eagley House, Deakins Business Park, Egerton, Bolton, Lancashire, BL7 9RP

Telephone 01204 565 500 Email enq@hardscape.co.uk

www.hardscape.co.uk