


Natural Stone / Sandstone / England / Forest Pennant | Blue

Forest Pennant


Blue

Sourced from a privately-owned natural stone quarry in the Forest of Dean, Gloucestershire, this selected blue Sandstone is durable and versatile.


SPECIFICATION	SKU: SAN-ENG-FPE-007	
Material	Sandstone	
Finish	Bush Hammered / Shotblasted, Honed, Sawn	
Density	-	2416 kg/m ³
GWP (total) kgCO ₂ e	ISO 14025 / EN 15804	-
Compressive Strength	BS EN 1926:2006	91 MPa LEV
Compressive Strength (Freeze/Thaw Resistance)	BS EN 1926:2006	91 / 109 MPa Mean
PPV (Before/After)	BS EN 7932:2003	Sawn 87/73 PPV
Flexural Freeze/Thaw	BS EN 12371:2010	15.5 / 12.9 MPa Mean
Flexural Strength	BS EN 12372:2006	15.5 MPa LEV
Light Reflectance Value	BS EN 84369:2008	Sawn 31.4 : Shotblasted 29.1 LRV
Open Porosity	BS EN 1936:2006	NPD
Slip Resistance	BS EN 13036-4, BS 7976	Diamond Sawn 80 (wet) : Flamed 89 (wet) SRV/USRV
Water Absorption	BS EN 13755:2008	2.6%
Abrasion Resistance	BS EN 14157:2004	20mm



Shotblasted



Honed



Sawn



Specification & technical data aligns with our most recent testing, but is indicative and should be treated as such. Images are for illustrative purposes only, exact colours may vary.