


Natural Stone / Granite / China / Magma | Multi

Magma


Multi

Our most popular alternative to sandstone in achieving a buff finish with the benefits of granite.


SPECIFICATION	SKU: GRA-CHI-MAG-039	
Material	Granite	
Finish	Bush Hammered, Flamed, Honed, Polished, Sandblasted, Sawn	
Density	-	2590 kg/m ³
GWP (total) kgCO ₂ e	ISO 14025 / EN 15804	0.129 per kg
Compressive Strength	BS EN 1926:2006	147 Mpa
Compressive Strength (Freeze/Thaw Resistance)	BS EN 1926:2006	160 / 167 Mpa
PPV (Before/After)	BS EN 7932:2003	Flamed 61/47, 72/59 PPV
Flexural Freeze/Thaw	BS EN 12371:2010	14.3 / 15.4 MPa
Flexural Strength	BS EN 12372:2006	11.6 MPa
Light Reflectance Value	BS EN 84369:2008	Bush Hammered 54.8 : Flamed 43.2 : Honed 42.2 Shotblasted 42.2 : LRV
Open Porosity	BS EN 1936:2006	1.3%
Slip Resistance	BS EN 13036-4, BS 7976	Bush Hammered 82 (wet), 90 (dry) Flamed 74 (wet), 79 (dry) SRV/USRV
Water Absorption	BS EN 13755:2008	0.4%
Abrasion Resistance	BS EN 14157:2004	20.1mm



Polished



Honed



Flamed



Bush Hammered



Specification & technical data aligns with our most recent testing, but is indicative and should be treated as such. Images are for illustrative purposes only, exact colours may vary.