

Natural Stone / Porphyry / Italy / Prima Porphyry | Violet Mix

Prima Porphyry

Grey Mix

A mineralogical content creates two dominant tones of grey-brown and grey-green. Used in various ways widely across Europe and the UK.



SPECIFICATION	SKU: POR-ITA-PPO-002	
Material	Porphyry	
Finish	Flamed, Honed, Polished, Sawn	
Density	-	2568 kg/m ³
GWP (total) kgCO ₂ e	ISO 14025 / EN 15804	0.248 per kg
Compressive Strength	BS EN 1926:2006	146 Mpa
Compressive Strength (Freeze/Thaw Resistance)	BS EN 1926:2006	185 / 194 Mpa
PPV (Before/After)	BS EN 7932:2003	Natural Cleft 73/53 PPV
Flexural Freeze/Thaw	BS EN 12371:2010	22.8 / 21.8 MPa
Flexural Strength	BS EN 12372:2006	21.6 MPa
Light Reflectance Value	BS EN 84369:2008	N/A
Open Porosity	BS EN 1936:2006	2.28%
Slip Resistance	BS EN 13036-4, BS 7976	Flamed 71 (wet), 92 (dry) : Natural Cleft 75 (wet), 87 (dry) SRV/USRV
Water Absorption	BS EN 13755:2008	0.9%
Abrasion Resistance	BS EN 14157:2004	15mm



Flamed



Specification & technical data aligns with our most recent testing, but is indicative and should be treated as such. Images are for illustrative purposes only, exact colours may vary.